


2₀₁₁₀84



MICROCOPY RESOLUTION TEST CHART NATIONAL BUREAU OF STANDARDS-1963-A

Approved for Public Release Distribution Unlimited DSTZT Report No. 82-13 AFPEA Project No. 81-P7-24



AD A 137287

ALFRED J. SICARD Mechanical Engineering Technician

AUTOVON 787-4519 Commercial (513) 257-4234

COST EFFECTIVENESS OF CUSHIONING MATERIALS FOR FAST PACKS



HQ AFLC/DSTZT
Air Force Packaging Evaluation Agency
Wright-Patterson AFB OH 45433

JANUARY 1984

OTTC FILE COPY

84 01 27 661

NOTICE

When government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related government procurement operation, the United States (iovernment thereby incurs no responsibility whatsoever; and the fact that the government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any pateried invention that may in any way be related thereto. This report is not to be used in whole or in part for advertising or vales purposes.

ABSTRACT

Consideration of potential cost savings as well as material availability problems resulted in the initiation of a study by this agency to reevaluate the polyurethane foam cushioning requirements specified in the Fast Pack specification PPP-B-1672. Additional emphasis was given to this study when the AFLC Spares Packaging Standardization Committee established and assigned an action item to AFPEA to determine whether the Grade C polyurethane foam currently specified for Fast Pack cushion inserts could be replaced with Grade B material which was less expensive and easier to obtain commercially. An extensive test program was conducted on the Type I, III, and IV Fast Packs in which the dynamic cushioning performance of both Grade B and C polyurethane cushion inserts were evaluated over the weight ranges currently specified in Appendix G of MIL-STD-794 for several of the different pack sizes. It was concluded that the substitution of Grade B polyurethane foam for Grade C foam could not be justified because of the significant reduction in the range of items that could be adequately protected.

ALFRED J. SICARD Mech Ingry Tech
Materials Engineering Division

REVIEWED AY Juther 6. Venetra

AF Packaging Evaluation Agency

MATTHEW A. VENETOS Chief, Materials Engineering Division AF Packaging Evaluation Agency PUBLICATION DATE:

09 JAN 1984

APPROVED BY

JACK E. THOMPSON

Director, Air Force Packaging

Evaluation Agency

TABLE OF CONTENTS

· · · · · · · · · · · · · · · · · · ·	Page
Abstract	i
Introduction	1
Equipment and Instrumentation	1
Test Loads	1
Description of Test Packs	2
Test Procedures	
A. Fast Pack Drop Test	2
B. Dynamic Compression Test of Polyurethane Foam Cushion Insert Materials	2
Results	3
Discussion/Conclusions	3
Recommendations	3
Figure 1: Gaynes Drop Tester & Instrumentation	4
Figure 2: Hardigg Cushioning Tester & Instrumentation	4
Figure 3: Typical Test Loads Used in Type I and II Fast Packs	5
Figure 4: Typical Test Loads Used in Type IV Fast Packs	5
Figure 5: Peak "G" - Static Stress Curves of Type I, 6 X 6 X 10 Fast Pack	6
Figure 6: Peak "G" - Static Stress Curves of Type I, 8 X 8 X 12 Fast Pack	7
Figure 7: Peak "G" - Static Stress Curves of Type I, 10 X 10 X 12 Fast Pack	8
Figure 8: Peak "G" - Static Stress Curves of Type I, 12 X 12 X 14 Fast Pack	9
Figure 9: Peak "G" - Static Stress Curves of Type I, 12 X 12 X 14 Fast Pack	10
Figure 10: Peak "G" - Static Stress Curves of Type I, 12 X 12 X 18 Fast Pack	11
Figure 11: Peak "G" - Static Stress Curves of Type I,14 X 14 X 16 Fast Pack	12

TABLE OF CONTENTS (Continued)

				Page
Figure 1			"G" - Static Stress Curves of Type I, 12 X 12 X 18 Pack	13
Figure 1			"G" - Static Stress Curves of Type III, 25 X 14 X 14 Pack	14
Figure 1	4: !	Peak Fast	"G" - Static Stress Curves of Type III, 30 X 16 X 14 Pack	15
Figure 1	5: i	Peak Fast	"G" - Static Stress Curves of Type III, 32 X 12 X 14 Pack	. 16
Figure 1			"G" - Static Stress Curves of Type IV, 20 X 14 X 14 Pack	. 17
Figure 1			"G" - Static Stress Curves of Type IV, 22 X 16 X 16 Pack	. 18
Figure 1			"G" - Static Stress Curves of Type IV, 22 X 16 X 16 Pack	. 19
Distribu	tion	List	t	. 20
DD Form	1473		• • • • • • • • • • • • • • • • • • • •	. 21



INTRODUCTION

This study was performed primarily to support the HQ AFLC/DSTP Spares Packaging Standardization Committee's effort to resolve shortages of fast pack containers reported throughout DOD. In addition AFPEA recognized the potential for reducing the cost of fast packs by substituting the less expensive Grade B polyurethane foam cushioning for the Grade C materials currently used. The shortage of fast packs stemmed from commercial manufacturers' difficulty in readily producing Grade C polyurethane foam meeting the dynamic cushioning characteristics specified in MIL-P-26514E. Consequently, the committee questioned whether Grade C foam as required in Federal Specification PPP-B-1672 for Type I, III and IV fast pack inserts was cost effective for the shock protection levels specified in Appendix G of MIL-STD-794D (Fast Pack Selection). It was noted that Grade B polyurethane foam, if used as an alternative, would cost less and would be more readily available from a larger number of manufacturers. The objective of this study was to determine if the proposed alternative Grade B polyurethane foam would provide protection comparable to that now obtained with the Grade C material.

EQUIPMENT AND INSTRUMENTATION

Evaluation of the fast packs and polyurethane foams used in the cushion inserts were performed with the following equipment and instrumentation:

- 1. Container drop tester, Gaynes, Model 125 DTP.
- 2. Cushion tester, Hardigg Industries, Model 3.
- 3. Compression Tensile tester, Instron TT-C.
- 4. Three Endevco crystal accelerometers, Model 2233E.
- 5. Three Endevco charge amplifiers, Model 2614C.
- 6. Endevco power supply, Model 2622C.
- 7. Tektronix four trace storage oscilloscope, Type 564B.
- 8. Statham stain gage accelerometer, Model A5-100-350.
- 9. GHI Energy Computer, Model EC700.
- 10. Sensotic power amplifier.

TEST LOADS

The prototype test loads (Figures 3 & 4) consisted of interchangeable wood, aluminum, lead and steel plates for the purpose of varying the weight. Each prototype load was instrumented with three crystal accelerometers, triaxially mounted at the center of gravity of the test load. The prototype loads were wrapped with 3 mil thick polyethylene film to reduce the friction between the load and cushion pad surfaces in order to avoid interference with the cushioning action of the polyurethane pads.

DESCRIPTION OF TEST PACKS

The exterior containers were fabricated from V3c corrugated fiberboard regular slotted containers conforming to specification PPP-B-636. The cushioning inserts in the pack were Type I, Class 2, Grade B and C, 1.5 pound density polyurethane foam meeting the dynamic cushioning properties specified in MIL-P-26514E. The type and size packs tested are identified in Figures 5 through 18. The fast packs were acquired from various air logistics center locations sampled from unused General Services Administration supply lots.

TEST PROCEDURES

Drop testing of Type I, III and IV fast packs containing Grades B and C polyurethane inserts, was performed during this study. The results obtained on these fast packs were then used to develop comparative Peak "G" - static stress curves depicted in Figures 5 through 18.

- A. Fast pack drop tests: Free fall drop tests were conducted in accordance with procedure B, Method 5007 of Federal Test Method Standard 101C, Level A (30-inch drop). Testing began with the lightest weight prototype loads and progressed to successively heavier weight loads. For each weight of prototype load five drops were made on each of the container's six faces. The drops were alternated between opposite side faces or opposite end faces, so that no face received two successive impacts. The peak G shock resultants for the end face impacts were averaged together for each load of a particular configuration; the same procedure was used for averaging the peak G shock resultants for the four side faces.
- B. Dynamic compression test of polyurethane foam cushion insert materials: The dynamic compression test of the polyurethane foam used in the fast packs was in accordance with paragraph 4.5.3.13 of MIL-P-26514E. Following completion of the fast pack drop testing, cushioning inserts (usually end pads) were removed from the containers and allowed to recover over a 72-hour period. Following the recovery period, three 8" x 8" x 3" specimens from each cushioning insert were cut and cyclically compressed ten times to 65 percent of their original thicknesses on an Instron compression tester. Inserts having convoluted surfaces (Type III fast packs) were cut flush and laminated with double face adhesive tape to make three-inch thick specimens. Following a 16 to 72-hour recovery period, the specimens were tested on the cushion drop tester. Each specimen was impacted by the drop platten of the cushion tester which compressed the specimens at an initial velocity of 136 +2 in/sec (24-inch drop height). The acceleration-time record of the impact was displayed on the CRT of the oscilloscope and the peak G values were measured and recorded for each drop. With drop platten weight at the lowest static stress value, five drops were made on each specimen allowing at least one minute between drops. Additional weight was added to the drop platten to obtain higher static stress points and the drop test procedure was repeated. Four static stress points (0.065, 0.15, 0.4, 0.8 psi) were selected to fully cover the range of the Grade B and C dynamic cushioning curves depicted in MIL-P-26514E. Peak acceleration values (Gs) within +20 percent of specification curve were considered as acceptable for verifying the material as either Grade B or Grade C polyurethane foam.

RESULTS

Based on the test results presented in Figures 5 through 18, it is apparent that Fast Packs utilizing Grade B foam will not provide the required shock protection over the entire weight ranges for Grade C foam specified in MIL-STD-794. It is estimated that Grade B foam inserts provided acceptable shock protection over only 61 percent of the weight ranges considered in Appendix G of MIL-STD-794. The reduced cushioning performance of Grade B foam in most cases was attributed to increased shock inputs occurring with the heavier items due to "bottoming out" of the cushion during repeated impacting.

DISCUSSION/CONCLUSIONS

Grade B foam Fast Pack inserts would afford shock protection levels equivalent to Grade C foam inserts over approximately 61 percent of the weight ranges currently specified in MIL-STD-794. This reduced effectiveness is considered to be contrary to the original purpose of the Fast Pack Program of providing optional shock protection to a maximum number of the diverse items in the DOD inventory.

The implementation of Grade B foam inserts into the Fast Pack Program would require retention of Grade C foam packs in the system to protect those items not afforded adequate protection by the Grade B foam. At least ten of the fourteen types—sizes of Grade C foam packs evaluated would probably have to be retained to complement the Grade B foam packs. This could result in redundancy in design and possible confusion resulting in the use of the wrong pack for an item.

Based on a survey of the major manufacturers of polyurethane foam it was determined that on average there is a 8.1 percent mark up in the cost of Grade C material over Grade B. During a one-year period approximately 3,000,000 board feet of Grade C polyurethane foam at a total cost of \$600,000 are used in the manufacture of Fast Packs for the Air Force. Therefore the substitution of Grade B for Grade C foam would result in a savings of \$45,000, assuming these savings are passed on to the government. It is believed that these savings are far outweighed by the potential consequences of replacing a proven pack with a less effective one which could result in damage to high value Air Force equipment.

Another consequence of introducing Grade B foam materials into the Fast Pack system would be the time, effort, and expense required to revise the Fast Pack selection tables in MIL-STD-794. Revision of these tables would require further extensive drop testing to develop complete data for all Type I, III and IV Fast Packs.

RECOMMENDATIONS

It is recommended that Grade C polyurethane foam requirement be continued for Type I, III and IV Fast Packs.




FIGURE 1. GAYNES DROP TESTER AND INSTRUMENTATION




FIGURE 2. HARDIGG CUSHIONING TESTER AND INSTRUMENTATION



FIGURE 3. TYPICAL TEST LOADS USED IN TYPE I AND II FAST PACKS




FIGURE 4. TYPICAL TEST LOADS USED IN TYPE IV FAST PACKS

. .




FIGURE 5.

PEAK ACCELERATION 20 40 10 30 50 0 GRADE B FOAM TEST DATA:
LOAD STATIC STRESS
WEIGHT - LOADING (END PAD)
3 lbs 0.25 PSI
5.8 0.46
7.9 0.62 FAST PACK TYPE I (VERTICAL STAR)
8" X 8" X 12", 2" THICK END PADS
TEST LOAD SIZE: 4" DIA X 8" LONG .0 . 24 Ιį, .06 RESULTS (Gs)
40 Gs 43 46 . 08 0.2 1 bs o.3 0.4 0.6 9 0.8 : Sq.

FIGURE 6

TEST RESULTS: GRADE B FOAM SHOCK LEVEL EXCEEDED THOSE OF GRADE C FOAM OVER THE FULL ITEM WEIGHT RANGE 3 TO 7.9 LBS.

STATIC STRESS-W/A (PSI)

-----GRADE "B" FOAM SHOCK PROTECTION LEVELS

LEGEND:

7

20

30

5

0

<u>.</u>

. 오

.06

. 08

4.9 LB WEIGHT RANGE; HOWEVER, IT

0.8

1.0


8


ğ

50









<u>0</u>.1 STATIC STRESS-W/A (PSI) 0.2 0.3 0.4 0.6

TEST RESULTS:
GRADE B FOAM PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS OVER THE 2 EXCEEDED THE SHOCK PROTECTION LEVEL OVER WEIGHT RANGE 4.9 TO 5.0 LBS. LEGEND:


ž

GRADE "C" FOAM SHOCK PROTECTION LEVELS

5.0 lbs

5 bs

L 1bs



TEST RESULTS: GRADE B FOAM SHOCK LEVEL EXCEEDED THOSE OF GRADE C FOAM OVER THE FULL ITEM WEIGHT RANGE 5 TO 13 LBS

.03

.04

.06

.08

0.1

0.3

0.4


0.6


0.8


1.0

STATIC STRESS-WA (PSI)

LEGEND:
-----GRADE "B" FOAM SHOCK PROTECTION LEVELS
------GRADE "C" FOAM SHOCK PROTECTION LEVELS







STATIC STRESS-W/A (PSI)

. 9

. 2

.06

.08

0.1

0.2

0.3

0.4

0.6

0.8

7.0

4.3 1bs

TEST RESULTS: GRADE B FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER THE ITEM WEIGHT RANGE 4.4 TO 8.5 LBS; HOWEVER FOR LOADS WEIGHING 3.5 TO 4.0 LBS IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS.

LEGEND:

;

GRADE "B" FOAM SHOCK PROTECTION LEVELS

6.6 1bs

8.5

1155

LEGEND:


-GRADE "B" FOAM SHOCK PROTECTION LEVELS
_GRADE "C" FOAM SHOCK PROTECTION LEVELS

TEST RESULTS: GRADE B FOAM PROVIDED EQUIVALENT SHOCK PROTECTION LEVELS OVER THE FULL ITEM WEIGHT RANGE 4 TO 11 LBS.

STATIC STRESS-W/A (PSI)

1.0

FIGURE 10




11

GRADE "B" FOAM SHOCK PROTECTION LEVELS

•

LEGEND: TEST RESULTS: GRADE B FOAM PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS OVER THE ITEM WEIGHT RANGE 7 TO 14 LBS; HOWEVER IT EXCEEDED THOSE SHOCK LEVELS OVER THE WEIGHT RANGE 14.1 TO 16 LBS



20

30

40

50

70

FIGURE 11

GRADE B FOAM TEST DATA:
LOAD . STATIC STRESS FAST PACK, TYPE I (VERTICAL STAR)
14" X 14" X 16", 3" THICK END PADS
TEST LOAD SIZE: 7" DIA X 10" LONG

STATIC STRESS LOADING (END PAD) . 0.273 0.400 0.486 SHOCK TEST RESULT (Gs) 27 23 25

WEIGHT 7.5 lbs 15.4 18.7

 ∞ Sq 14.3 1bs 18.7 20

. 9

.04

.06

.08

0.1

0.2

0.3

0.4

0.6

0.8

STATIC STRESS-WA (PSI)

11:

TEST RESULTS: GRADE B FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER THE ITEM WEIGHT RANGE 7.5 TO 12.4 LBS; HOWEVER, FOR LOADS WEIGHING 12.3 TO 20 LBS, IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS. LEGEND: --GRADE "B" FOAM SHOCK PROTECTION LEVELS

Sq

Sq

TEST RESULTS: GRADE B FOAM PROVIDED EQUIVALENT SHOCK PROTECTION LEVELS OVER THE FULL RANGE 7.4 TO 29.4 LBS.

FAST PACK, TYPE III (TELESCOPING)
25" X 14" X 14", 6" THICK END PADS
TEST LOAD SIZE: L13" X 7"W X 7"D





FIGURE 14



GRÂDE B FOAM PROVIDED EQUAL OR BETTER SHOCK PROTECTION OVER THE WEIGHT RANGE 28 - 47 LBS; HOWEVER FOR LOADS ABOVE 47 LBS IT EXCEEDED GRADE C FOAM SHOCK LEVELS. LEGEND:

TEST RESULTS:

.0

. 2

. 8

. 8

0.7

0.2

0.3

0.4

0.6

0.6

7.0

STATIC STRESS-W/A (PSI)

GRADE "C" FOAM SHOCK PROTECTION LEVELS

28 1bs

47 1bg

52 7bs

TEST RESULTS: GRADE B FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER THE ITEM WEIGHT RANGE 22 TO 32 LBS; HOWEVER, FOR LOADS WEIGHING 14 TO 22 LBS, IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS.

STATIC STRESS-W/A (PSI)


7.0

LEGEND:

GRADE "C"

FOAM SHOCK PROTECTION

LEVELS



16


LEGEND:

GRADE "B" FOAM SHOCK PROTECTION LEVELS

TEST RESULTS:

GRADE B FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER THE ITEM WEIGHT RANGE 15.5 TO 21 LBS; HOWEVER, FOR LOADS WEIGHING 6 TO 15.5 LBS, IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS.

FIGURE 16



17

ω 7

14 1hs

<u>.</u>

<u>.</u>

8

. 8

0.1

0.2

0.3

.0.4

0.6


0,8

!:

STATIC STRESS-W/A (PSI)

1

ŧ



29

.51bs

TEST RESULTS: GRADE 8 FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER ITEM WEIGHT RANGE ABOVE 14 TO 29.5 LBS; HOWEVER, FOR LOADS WEIGHING 14 TO 8 LBS, IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS. GRADE "C" FOAM SHOCK PROTECTION LEVELS

30

40

50

20

10

<u>.</u>

.04

.06

.08

0.1

FIGURE 18

FAST PACK, TYPE IV (HORIZ. STAR)
22" X 16" X 16", 3" THICK END PADS
TEST LOAD SIZE: 16" X 7%" X 7%"

MEIGHT MEIGHT GRADE B FOAM TEST DATA: STATIC STRESS
LOADING (END PAD)
0.21 PSI
0.28
0.49
0.49
0.60

LOAD

SHOCK TEST RESULT (Gs)

14.8 26.0 31.8

1bs 0.2

STATIC STRESS-W/A (PSI)

0.3 0.4 0.6

Sq 0,8 7.0

TEST RESULTS: GRADE B FOAM EXCEEDED THE SHOCK PROTECTION LEVELS OVER ITEM WEIGHT RANGE 28 TO 31 LBS; HOWEVER, FOR LOADS WEIGHING 11 TO 28 LBS IT PROVIDED EQUAL OR BETTER SHOCK PROTECTION LEVELS.

LEGEND:

GRADE "B" FOAM SHOCK PROTECTION LEVELS

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE							
18. REPORT SECURITY CLASSIFICATION		16. RESTRICTIVE MARKINGS					
Unclassified		N/A					
2& SECURITY CLASSIFICATION AUTHORITY N/A		3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for Public Release					
26. DECLASSIFICATION/DOWNGRADING SCHED		Distribution Unlimited					
4. PERFORMING ORGANIZATION REPORT NUM	BÉR(\$)	5. MONITORING OR	GANIZATION RE	PORT NUMBER	(8)		
DSTZT Report No. 82-13		N/A					
64 NAME OF PERFORMING ORGANIZATION	6b. OFFICE SYMBOL (If applicable)	74. NAME OF MONITORING ORGANIZATION					
Air Force Packaging Evaluation Agency	HQ AFLC/DSTZT	N/A					
6c. ADDRESS (City, State and ZIP Code)	THE MERCY DOTE	N/A 7b. ADDRESS (City, State and ZIP Code)					
Wright-Patterson AFB OH 45433		N/A					
to. NAME OF FUNDING/SPONSORING ORGANIZATION	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER					
N/A	N/A	N/A					
Sc. ADDRESS (City, State and ZIP Code)	A.————————————————————————————————————	10. SOURCE OF FUN	IDING NOS.				
N/A	I	PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT NO.		
11. TITLE (Include Security Classification) COST Of Cushioning Materials For Fas		N/A	N/A	N/A	N/A		
12. PERSONAL AUTHOR(S)		L					
Alfred J. Sicard							
13a TYPE OF REPORT 13b. TIME C		14. DATE OF REPOR					
Final FROM	TO	_ January 1984		26			
N/A							
17. COSATI CODES	18 SUBJECT TERMS (C	ontinue on reverse if ne	cemary and identi	ly by block numb	Mer)		
FIELD GROUP SUB. GR.		. SUBJECT TERMS (Continue on reverse if necessary and identify by block number) Polyurethane Foam Drop Test					
13 04	Fast Pack				est		
	<u> </u>	Commission		44-74			
19. ABSTRACT (Continue on reverse if necessary and well as material availability							
agency to reevaluate the polyu	rethane foam cus	shionina requi	rements spe	ecified in	the Fast		
Pack specification PPP-B-1672,	Additional emp	ohasis was giv	en to this	study whe	n the AFLC		
Spares Packaging Standardizati	on Committee est	tablished and	assigned a	n action i	tem to		
AFPEA to determine whether the Grade C polyurethane foam currently specified for Fast Pack							
cushion inserts could be replaced with Grade B material which was less expensive and							
easier to obtain commercially. An extensive test program was conducted on the Type I, III, and IV Fast Packs in which the dynamic cushioning performance of both Grade B and C							
polyurethane cushion inserts were evaluated over the weight ranges currently specified in							
Appendix G of MIL-STD-794 for several of the different pack sizes. It was concluded that							
the substitution of Grade B polyurethane foam for Grade C foam could not be justified							
because of the significant reduction in the range of items that could be adequately protected.							
20. DISTRIBUTION/AVAILABILITY OF ASSTRA	21. ABSTRACT SECURITY CLASSIFICATION						
UNCLASSIFIED/UNLIMITED 🗵 SAME AS RPT.	UNCLASSIFIED						
226. NAME OF RESPONSIBLE INDIVIDUAL 226. TELEPHONE NUMBER 22c. OFFICE SYMBOL				MBOL			
Alfred J. Stcard .	(Include Area Co 513-257-4519		HQ AFLC/	DSTZT			

DISTRIBUTION LIST

ADTC/YXC		DLSIE/DRXMC-D	
Eglin AFB FL 32542	1	US Army Logistics Management	
		Attn: Mr. Malcom Alley	
AFALC/PTPP		Fort Lee VA 23801	1
WPAFB OH 45433	3		
		DTIC/TSR	
AFCMD/PDT		Cameron Station	
Attn: Jim Rorie		Alexandria VA 22314	12
Kirtland AFB NM 87115	3		
	•	ESD/TOSM	
AFPRO/PD (Packaging Engineer)		Hanscom MA 01731	1
Westinghouse Defense &			
Electronic System Center		GSA, Ofc of Engineering	
P.O. Box 1693		Management	
Baltimore MD 21203	1	Packaging Division	
Date more mo 21203	ı	WASH DC 20401	1
ACDDA/DD D A Day 271		William Do Lovo!	•
AFPRO/PD, P.O. Box 371		HQ AFLC/DSTP	
General Dynamics		WPAFB OH 45433	1
Attn: Rick Stenzil		HTALD 011 4353	
Ft Worth Division		UO AEI CIDSTAT	
Ft Worth TX	1	HQ AFLC/DSTZT	
100 /10 /D 11		Project Folder	,
ASD/AEWS (D. Murray)	_	WPAFB OH 45433	1
WPAFB OH 45433	1	UO AELO/DOTTE L'Ibro-	
		HQ AFLC/DSTZT Library	00
ASD/AWL		WPAFB OH 45433	20
WPAFB OH 45433	7	110 4 700 11 07	
		HQ AFSC/LGT	_
ASD/YPL		Scott AFB IL 62225	1
Attn: J. Hartley			
Lt R. Weldon		HQ DLA-OWO	
WPAFB OH 45433	7	Cameron Station	
		Alexandria VA 22314	1
ASO/TEP-A 4030			
700 Robbins Avenue		HQ USAF/LETT	
Philadelphia PA 19111	1	WASH DC 20330	
Aviation Supply Office		Naval Weapons Support Center	
Attn: Engrg Div		Code 505 (F. Niehaus)	
700 Robbins Avenue		Crane IN 47522	1
Philadelphia PA 19111	1		
	•	NAVSUPSYCMD	
DARCOM, Packaging &		Attn: SUP-0321A	
Storage & Containerization Cen	itar	WASH DC 20376	5
Attn: SDSTO-T	1461	·····	
Tobyhanna PA 18466	1	OC-ALC/DSP	
TODY Halling FA 10700	1	TINKER AFB OK 73145	1
DESC-T		tendent in a Aut tenia	•
1507 Wilmington Pike		00-ALC/DSP	
	•	HILL APB UT 84056	1
Dayton OH 45444	7	HIPP WIR AT GARAGE	'

DISTRIBUTION LIST (CONT)

PRC		US Army Armament Research	
13837 Bettencourt Street		& Development Command	
Cerritos CA 90701	1	Attn: DRDAR-TST-S	
		Dover NJ 07801	1
SAMSO/AWL			
Norton AFB CA 92409	1	US Army Natick Labs	
		Attn: DRDNA-EPS	
SA-ALC/DSP		Natick MA 01760	1
KELLY AFB TX 78241	1		
		WR-ALC/DSP	
SM-ALC/DSP		ROBINS AFB GA 31098	1
MCCLELLAN AFB CA 95642	1		

MED - S